


FOLIEFOL® MULTITOP XS


Construction membrane
for installation on
the cold side.

GENERAL

Foliefol® Multitop XS is a three-layer watertight (W1) and breathable membrane, composed of two layers of Polypropylene with the functional microporous film in between. Foliefol® Multitop XS complies with the European standard EN 13859-1 & EN 13859-2.

Foliefol® Multitop XS is available in the following dimensions:

Dimensions	Article number	EAN-code
1,50 x 50 meters	DWF10150-2015	8713331013664
3,00 x 50 meters	DWF10150-2030	8713331013688

APPLICATION

Foliefol® Multitop XS is used as a watertight, vapor open layer on the cold side (usually the exterior) of roof and wall structures in new buildings and renovation. In roofs and walls, Foliefol® Multitop XS can be applied directly to hard and soft surfaces. If there is no hard roof boarding (e.g. OSB), a maximum center-to-center distance of the beams of 60 cm must be taken into account. For a larger center-to-center distance please contact Berdal for tailor-made advice.

PRODUCT PROPERTIES


Roof



Hard surface



Maximum period of application 3 months



Vapour open



Facade



Soft surface



Bears weight of one person



Waterproof

Essential characteristics	
Mass per unit area	150 gr/m ²
Reaction to fire [class]	E
Resistance to water penetration [class]	W1
Water vapour resistance (Sd)	0,02 [m] (-0,005/+0,02)
Tensile strength before artificial ageing	350 [N/50mm] (-90/+90) – MD 225 [N/50mm] (-25/+70) – CD
Tensile strength after artificial ageing	290 [N/50mm] (-60/+60) – MD 180 [N/50mm] (-30/+30) – CD
Elongation before artificial ageing	70 [%] (-40/+40) – MD 105 [%] (-55/+55) – CD
Elongation after artificial ageing	40 [%] (-20/+20) – MD 60 [%] (-25/+25) – CD
Resistance to tearing	185[N] (-70/+70) – MD 205 [N] (-80/+80) – CD
Flexibility at low temperature	-40 [°C]

INSTALLATION

Lay the membrane in an imbricated pattern, whereby the horizontal overlaps should be at least 150 mm. For roof pitches <22 ° an overlap of 200mm is recommended. Minimum possible roof pitch is 18 °. The membrane should be attached to the structure using stainless steel staples (min. length 8 mm) and then counter battens should be applied over the staples. Tape overlaps using Foliefol® Multitop tape or adhere using Foliefol® double-sided tape. Always apply Foliefol® Multitop XS with the printed side legible from the outside. On roof gradients between 18° and 22°, Foliefol® Nageldichtband (foam tape) should be applied under the counter battens. It is recommended to avoid vertical connections. Place any vertical overlaps between a batten/counter batten and an underlying rib/ post or glue the overlaps. If the roof pitch is > 22 °, maintain a width of the overlap of at least the rib /post width, whereby this must protrude at least one width of the counter batten. If 18 ° > roof pitch <22 °: the vertical seam must be applied under the batten, whereby the Foliefol® Nail Sealing Tape is adhered over the middle of the seam and then the batten is applied to it. At corners, the membrane should be continued to the next upright and then attached to it with staples and, if necessary, a counter batten. Apply the membrane at the roof base in such a way that any leakage water disappears into the gutter. Immediately repair any damage to the membrane using Foliefol® Multitop tape. Adhere joining using Foliefol® doublesided tape, Foliefol® butyl tape or Foliefol® foil adhesive. Cover the membrane as soon as possible after application (within the mentioned open working time). Protect the membrane from direct exposure to wood impregnation agents. Avoid laying the membrane directly on freshly impregnated elements in any circumstances.

RELATED PRODUCTS

Productname	Dimensions	Article number	EAN-code
Foliefol® Multitop spinvlies tape	0,06 x 25 meters	VPM10300-9030	8713331000275
Foliefol® Butyltape	0,02 x 15 meters	VPM10300-9040	8713331028842
Foliefol® Nageldichtband 3 mm	0,06 x 30 meters	VPM10300-9070	8713331015354